


STA.290




STA.280



STA.420



STA.850



STA.830



STA.430



STA.270



STA.260




STA.250



STA.220



STA.230



STA.240



STA.870



STA.880

STARTWIST EDITION

lano carpets residential

Fabricagemethode Technique de fabrication Manufacturing process Herstellungsart Tecnica di fabbricazione **tufted, 1/8" twist**	Poolsamenstelling Nature du velours Pile composition Polmaterial Composizione felpa **PP**	Rugtype Envers Secondary backing Rücken Sottofondo **SB**	Breedte Largeur Width Breite Altezza **± 400 & 500 cm**
Totale dikte Hauteur totale Total height Gesamthöhe Spessore totale **± 8,0 mm**	Nuttige poolhoogte Hauteur de velours utile Effective pile height Tatsächliche Florhöhe Spessore felpa utile **± 6,0 mm**	Aantal noppen/m^2 Nombre de points/m^2 Number of knots/sqm Noppenzahl/m^2 Numero di punti/mq **± 144900**	Poolinzetgewicht/m^2 Poids mis en oeuvre/m^2 Pile weight/sqm Poleinsatzgewicht/m^2 Peso felpa/mq **± 1020 gr**
Totaal gewicht/m^2 Poids total/m^2 Total weight/sqm Gesamtgewicht/m^2 Peso totale/mq **± 1970 gr**	**BS 4790** Brandgedrag Comportement au feu Fire behaviour Brennverhalten Reazione al fuoco **E_{fl}-s1**	**ISO 105 B02 2000** Lichtechtheid Solidité à la lumière Lightfastness Lichtechtheid Solidità colori alla luce **≥ 5-6**	**ISO 105 E01 2002** Waterechtheid verkleuring Solidité à l'eau changement couleur Waterfastness change in colour Wasserechtheit Änderung der Farbe Solidità colori all'acqua cambio colore **≥ 3-4**
ISO 105 E01 2002 Waterechtheid uitbloeding Solidité à l'eau dégorgement Waterfastness staining Wasserechtheit anbluten Solidità colori all'acqua sfumatura colore **≥ 3**	**ISO 105 X12 2001** Wrijfechtheid droog Solidité au frottement sec Rubbingfastness dry Reibungechtheit trocken Solidità colori allo sfregamento a secco **≥ 3-4**	**ISO 105 X12 2001** Wrijfechtheid nat Solidité au frottement humide Rubbingfastness wet Reibungechtheit nass Solidità colori allo sfregamento umido **≥ 2-3**	

(±) These details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request. We reserve the right to improve technical specifications without prior notice. Due to method of manufacture perfect pattern and/or colour matching cannot be guaranteed. In cut-pile carpeting, in rare cases, shading/pile reversal may occur without affecting its fitness for use. Shading/pile reversal can not be considered as a manufacturing or a material defect and will not affect the durability of the carpet.
For other languages see: www.lano.com

Recommended installation All over direct stick down with EC1 approved adhesive. Lay in accordance with BS 5325 2001. Correct seam sealing adhesive is necessary to prevent seam break-downs.
Cleaning & Maintenance Vacuum for normal day to day cleaning. Commercial cleaning using either dry chemical extraction or the hot water extraction method is recommended when required depending on local conditions. The use of castor chair mats will significantly improve the long term appearance of the carpet. Due to dye lot variations, actual material may vary slightly from sample. Bleach based cleaning solutions may be used on this product. Direct sunlight may cause damage to carpets.

The Green signature of Lano Carpets

ÉMISSIONS DANS L'AIR INTÉRIEUR A+ A+ A B C

REACH The new EU chemicals legislation

CE
DOP-CPR-1116-122201
EN 14041
E_{fl} DS
EN 1307

NO SHOCK

100% PP

ISO 9001

BQA_QMS019_C_199460